Technical Information

Comparison table materials	**D2-D8**
Comparison table hardness and tensile strength	**D9-D10**
Example of materials for machining groups	**D11**
Torque for screw	**D12**

D

Comparison table materials

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
P	Alloy steel											
	15	1015	1.0401	C15	080M15	–	1350	CC12	C15C16	F.111	–	
	20	1020	1.0402	C22	050A20	2C	1450	CC20	C20C21	F.112	–	20
	35	1035	1.0501	C35	060A35	–	1550	CC35	C35	F.113	–	35
	45	1045	1.0503	C45	080M40	–	1650	CC45	C45	F.114	–	45
	55	1055	1.0535	C55	070M55	–	1655	–	C55	–	–	55
	60	1060	1.0601	C60	080A62	43D	–	CC55	C60	–	–	60
	Y15	1213	1.7015	9SMn28	230M07	–	1912	S250	CF9SMn28	11SMn28	SUM22	15Ch
	–	12L13	1.0718	9SMnPb28	–	–	1914	S250Pb	CF9MnPb28	11SMnPb28	SUM22L	–
	–	–	1.0722	10SPb20	–	–	–	10PbF2	CF10Pb20	10SPb20	–	–
	–	1140	1.0726	35S20	212M36	8M	1957	35MF4	–	F210G	–	–
	Y13	1215	1.0736	9SMn36	240M07	1B	–	S300	CF9SMn36	12SMn35	–	–
	–	12L14	1.0737	9SMnPb36	–	–	1926	S300Pb	CF9SMnPb36	12SMnP35	–	–
	55Si2Mn	9255	1.0904	55Si9	250A53	45	2085	55S7	55Si8	56Si7	–	–
	–	9262	1.0961	60SiCr7	–	–	–	60SC7	60SiCr8	60SiCr8	–	–
	15	1015	1.1141	Ck15	080M15	32C	1370	XC12	C16	C15K	S15C	15
	40Mn	1039	1.1157	40Mn4	150M36	15	–	35M5	–	–	–	40G
	25	1025	1.1158	Ck25	–	–	–	–	–	–	S25C	25
	35Mn2	1335	1.1167	36Mn5	–	–	2120	40Mn5	–	36Mn5	SMn438(H)	35G2,35GL
	30Mn	1330	1.1170	28Mn6	150M28	14A	–	20M5	C28Mn	–	SCMn1	30G
	35Mn	1035	1.1183	Cf35	060A35	–	1572	XS38TS	C36	–	S35C	–
	Ck45	1045	1.1191	45	080M46	–	1672	XC42	C45	C45K	S45C	–
	55	1055	1.1203	Ck55	070M55	–	–	XC45	C50	C55K	S55C	55
	50	1050	1.1213	Cf53	060A52	–	1674	XC48TS	C53	–	S50C	–
	60Mn	1060	1.1221	Ck60	080A62	43D	1678	XC60	C60	–	S58C	60,60G
	–	1095	1.1274	Ck101	060A96	–	1870	–	–	–	SUP4	–
	–	–	1.3401	X120Mn12	Z120M12	–	–	X120M12	XG120Mn12	X120Mn12	SCMnH/1	110G13L
	Gr15;45Gr	52100	1.3505	100Cr6	534A99	31	2258	100C6	100Cr6	F.131	SUJ2	SchCh 15
	–	ASTM A204Gr.A	1.5415	15Mo3	1501-240	–	2912	15D3	16Mo3KW	16Mo3	–	–
	–	4520	1.5426	16Mo5	1503-245-420	–	–	–	16Mo5	16Mo5	–	–
	–	ASTM A350LF5	1.5622	14Ni6	–	–	–	16N6	14Ni6	15Ni6	–	–
	–	ASTM A353	1.5662	X8Ni9	1501-509;510	–	–	–	X10Ni9	XBNi09	–	–

Comparison table materials

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
P	**Alloy steel**											
	–	2515	1.5680	12Ni19	–	–	–	Z18N5	–	–	–	–
	–	3135	1.5710	36NiCr6	640A35	111A	–	35NC6	–	–	SNC236	–
	–	3415	1.5732	14NiCr10	–	–	–	14NC11	16NiCr11	15NiCr11	SNC415(H)	–
	–	3415 3310	1.5752	14NiCr14	655M13 655A12	36A	–	12NC15	–	–	SNC815(H)	–
	–	9840	1.6511	36CrNiMo4	816M40	110	–	40NCD3	38CrNiMo4(KB)	35CrNiMo4	–	40 ChN2MA
	–	8620	1.6523	21NiCrMo2	850M20	362	2503	20NCD2	20NiCrMo2	20NiCrMo2	SNCCM220(H)	–
	–	8740	1.6546	40NiCrMo2	311-Type7	–	–	–	40NiCrMo2(KB)	40NiCrMo2	SNC240	38ChGNM
	40CrNiMoA	4340	1.6582	34CrNiMo6	817M40	24	2541	35NCD6	35CrNiMo6(KB)	–	–	38Ch2N2MA
	–	–	1.6587	17CrNiMo6	820A16	–	–	18NCD6	–	14CrNiMo13	–	–
	15Cr	5015	1.7015	15Cr3	523M15	–	–	12C3	–	–	SCr415(H)	15Ch
	35Cr	5132	1.7033	34Cr4	530A32	18B	–	32C4	34Cr4(KB)	35Cr4	SCr430(H)	35Ch
	40Cr	5140	1.7035	41Cr4	530M40	18	–	42C4	41Cr4	42Cr4	SCr440(H)	40Ch
	40Cr	5140	1.7045	42Cr4	–	–	2245	–	–	42Cr4	SCr440	40Ch
	18CrMn	5115	1.7131	16MnCr15	(527M20)	–	2511	16MC5	16MnCr15	16MnCr15	–	18ChG
	20CrMn	5155	1.7176	55Cr3	527A60	48	–	55C3	–	–	SUP9(A)	50ChGA
	30CrMn	4130	1.7218	25CrMo4	1717CDS110	–	2225	25CD4	25CrMo4(KB)	55Cr3	SCM420; SCM430	30ChM
	35CrMo	4137;4135	1.7220	34CrMo4	708A37	19B	2234	35CD4	35CrMo4	34CrMo4	SCM432; SCRRM3	AS38ChGM
	40CrMoA	4140;4142	1.7223	41CrMo4	708M40	19A	2244	42CD4TS	41CrMo4	41CrMo4	SCM440	40 ChFA
	42CrMo 42CrMnMo	4140	1.7225	42CrMo4	708M40	19A	2244	42CD4	42CrMo4	42CrMo4	SCM440(H)	–
	–	–	1.7262	15CrMo5	–	–	2216	12CD4	–	12CrMo4	SCM415(H)	–
	–	ASTM A182 F11;F12	1.7335	13CrMo44	1501- 620Gr.27	–	–	15CD3.5; 15CD4.5	14CrMo44	14CrMo45	–	12ChM , 15ChM
	–	–	1.7361	32CrMo12	722M24	40B	2240	30CD12	32CrMo12	F.124.A	–	–
	–	ASTM A182 F.22	1.7380	10CrMo910	1501- 622Gr.31;45	–	2218	12CD9;10	12CrMo9,10	TU.H	–	–
	–	–	1.7715	14MoV63	1503-660-440	–	–	–	–	13MoCrV6	–	–
	50CrVA	6150	1.8159	50CrV4	735A50	47	2230	50CV4	50CrV4	51CrV4	SUP10	50ChGFA
	–	–	1.8509	41CrAlMo7	905M39	41B	2940	40CAD6,12	41CrAlMo7	41CrAlMo7	–	38ChMJuA
	–	–	1.8523	39CrMoV139	897M39	40C	–	–	36CrMoV12	–	–	–

Comparison table materials

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/ SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
P	Alloy steel											
	T10	W.110	1.1545	C105W1	–	–	1880	Y1105	C98KU C100KU	F.515 F.516	–	U10A
	T12A	W.112	1.1663	C125W	–	–	–	Y2120	C120KU	(C120)	SK2	U13
	CrV;9SiCr	L3	1.2067	100Cr6	BL3	–	–	Y100C6	–	100Cr6	–	–
	Cr12	D3	1.2080	X210Cr12	BD3	–	–	Z200Cr12	X210Cr13KU X250Cr12KU	X210Cr12	SKD1	Ch12
	4Cr5MoVSi	H13	1.2344	X40CrMoV5 1	BH13	–	2242	Z40CDV5	X35CrMoV05KU X40CrMoV51KU	X40CrMoV5	SKD61	4Ch5MF1S
	Cr6WV	A2	1.2363	X100CrMoV5 1	BA2	–	2260	Z100CDV5	X100CrMoV51KU	X100CrMoV5	SKD12	–
	CrWMo	–	1.2419	105WCr6	–	–	2140	105WC13	10WCr6 107WCr5KU	105WCr5	SKS31 SKS2 SKS3	ChWG
	Cr12W	–	1.2436	X210CrW12	–	–	2312	–	X215CrW12 1KU	X210CrW12	SKD2	–
	5CrNiMo	S1	1.2542	45WCrV7	BS1	–	2710	–	45WCrV8KU	45WCrSi8	–	–
	3Cr2W8V	H21	1.2581	X30WCrV9 3 X30WCrV93KU	BH21	–	–	Z30WCV9	X28W09KU X30WCrV9 3KU	X30WCrV9	SKD5	3Ch2W8F
	Cr12MoV	–	1.2601	X165CrMoV 12	–	–	2310	–	X165CrMoW12KU	X160CrMoV12	SKD11	–
	5CrNiMo	L6	1.2713	55NiCrMoV6	–	–	–	55NCDV7	–	F.250.S	SKT4	5ChNM
	V	W210	1.2833	100V1	BW2	–	–	Y1105V	–	–	SKS43	–
	W6Mo5Cr4V2Co5	–	1.3243	S6-5-2-5	–	–	2723	Z85WDKCV	HS6–5–2–5	HS6-5-2-5	SKH55	R6M5K5
	W18Cr4VCo5	T4	1.3255	S18-1-2-5	BT4	–	–	Z80WKCV 10-05-04-01	X78WCo1805KU	HS18-1-1-5	SKH3	–
	W6Mo5Cr4V2	M2	1.3343	S6-5-2	BM2	–	2722	Z85WDCV 06-05-04-02	X82WMo0605KU	HS6-5-2	SKH9	R6M5
	–	M7	1.3348	S2-9-2	–	-Z-	2782	Z100WCWV 09-02-04-02	HS2-9-2	HS2-9-2	–	–
	W18Cr4V	T1	1.3355	S18-0-1	BT1	–	–	Z80WCV 18-04-01	X75W18KU	HS18-0-1	SKH2	–
	W6Mo5Cr4V3	M3	–	S6-5-3	–	–	–	–	–	–	SKH52	–
	–	M42	–	–	BM42	–	–	–	–	–	SKH59	–

Comparison table materials

ISO	Country and standard						Main application
	China	USA	Germany	Japan	Daido Steel Co., Ltd (Japan)	Russia	
	GB	AISI/SAE	DIN	JIS	DAIDO	GOST	
P	**Plastic die steel**						
	–	P20 mod.		–	PX5N		For mass production of large mirror dies. Automobile tail light, front fender of car, video camera, household electrical appliances etc
	–	–		–	NAK55		High precision mirror die. Video camera, music disc, Cosmetic Containers, transparent covers, transparent films etc
	–	–		–	NAK80		High precision mirror die. Video camera, music disc, Cosmetic Containers, transparent covers, transparent films etc
	3Cr13	420 mod.		SUS420J2 mod.	S-STAR		For ultra-mirror corrosion resistant precise dies. Accessories of camera, CD, lens, watch case.
	Cold-working die steel						
	–	02	–	SKS93	YK30		Stamping die, gauge calipers, paper cutter, auxiliary tools
	9CrWMn	01 mod.	–	SKS3 mod.	GOA		Blanking die, gauge calipers, drawing die, taps, Perforated punch.
	Cr12MoV	D2	X165CrMoV12	SKD11	DC11		Blanking die, cold forming die, cold drawing die, forming roller, punch
	–	D2 mod.	–	SKD11 mod.	DC53		Blanking die, cold forming die, cold drawing die, forming roll, punch
	Hot-working die steel						
	4Cr5MoSiV1	H13	X40CrMoV51	SKD61	DHA1		Aluminum-compression die, connecting parts of compression die, hot stamping die, hot extrusion die, thermal shear cutting blade
	–	–	–	–	DH21		Long life Aluminum compression die
	–	–	–	–	DH31-S		Compression die
	–	–	–	–	DH2F		Compression die, plastic die

Comparison table materials

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/ SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
M	**Stainless steel**											
	0Cr13; 1Cr12	403	1.4000	X6Cr13	403S17	–	2301	Z6C13	X6Cr13	F.3110	SUS403	08Ch13
	–	–	1.4001	X7Cr14	–	–	–	–	–	F.8401	–	–
	1Cr13	410	1.4006	X10Cr13	410S21	56A	2302	Z10C14	X12Cr13	F.3401	SUS410	12Ch13
	1Cr17	430	1.4016	X6Cr17	430S15	60	220	Z8C17	X8Cr17	F.3113	SUS430	12Ch17
	2Cr13	410	1.4021	X20Cr13	S62	56B; 56C	–	Z20C13	X20C13	F.3401	SUS410	20Ch13
	–	–	1.4027	G-X20Cr14	420C29	56B	–	Z20C13M	–	–	SCS2	20Ch13L
	4Cr13	–	1.4034	X46Cr13	420S45	56D	2304	Z40CM Z38C13M	X40Cr14	F.3405	SUS420J2	40Ch13
	1Cr17Ni2	431	1.4057	X20CrNi172	431S29	57	2321	Z15CNi6.02	X16CNi16	F.3427	SUS431	20Ch17N2
	Y1Cr17	430F	1.4104	X12CrMoS17	–	–	2383	Z10CF17	X10CrS17	F.3117	SUS430F	–
	1Cr17Mo	434	1.4113	X6CrMo171	434S17	–	2325	Z8CD17.01	X8CrMo17	–	SUS434	–
	–	–	1.4313	X5CrNi134	425C11	–	–	Z4CND13.4M	–	–	SCS5	–
	–	–	1.4408	G-X6CrNiMo1810	316C16	–	–	–	–	F.8414	SCS14	07Ch18N10G2S2M2L
	4Cr9Si2	HW3	1.4718	X45CrSi93	401S45	52	–	Z45CS9	X45CrSi8	F.322	SUH1	40Ch9S2
	0Cr13Al	405	1.4724	X10CrAl13	403S17	–	–	Z10C13	X10CrAl12	F.311	SUS405	10Ch13SJu
	Cr17	430	1.4742	X10CrAl18	430S15	60	–	Z10CAS18	X8Cr17	F.3113	SUS430	15Ch18SJu
	8Cr20Si2Ni	HNV6	1.4757	X80CrNiSi20	443S65	59	–	Z80CSN20.02	X80CrSiNi20	F.320V	SUH4	–
	2Cr25N	446	1.4762	X10CrAl24	–	–	2322	Z10CAS24	X16Cr26	–	SUH446	–
	Austenitic stainless steel											
	0Cr18Ni9	304	1.4301	X5CrNi1810	304S15	58E	2332	Z6CN18.09	X5CrNi1810	F.3551; F.3541; F.3504	SUS304	08Ch18N10
	1Cr18Ni9MoZr	303	1.4305	X10CrNiS189	303S21	58M	2346	Z10CNF18.09	X10CrNiS18.09	F.3508	SUS303	–
	0Cr19Ni10	304L	1.4306	X2CrNi1911	304S12	–	2352	Z2CN18.10	X2CrNi18.11	F.3503	SCS19	03Ch18N11
	–	–	1.4308	G–X6CrNi189	304C15	–	–	Z6CN18.10M	–	–	SCS13	07Ch18N9L
	Cr17Ni7	301	1.4310	X12CrNi177	–	–	2331	Z12CN17.07	X12CrNi1707	F.3517	SUS301	–
	–	304LN	1.4311	X2CrNiN1810	304S62	–	2371	Z2CN18.10	–	–	SUS304LN	–
	0Cr19Ni9	304	1.4350	X5CrNi189	304S31	58E	–	Z6CN18.09	X5CrNi1810	–	SUS304	–
	0Cr17Ni11Mo2	316	1.4401	X5CrNiMo1712	316S16	Z6CND17.11	2347	1.4401	X5CrNiMo1712	F.3543	SUS316	–
	00Cr17Ni13Mo2	316LN	1.4429	X2CrNiMoN17133	–	–	2375	Z2CND17.13	–	–	SUS316LN	–
	0Cr27Ni12Mo3	316L	1.4435	X2CrNiMo18143	316S12	–	2353	Z2CDN17.13	X2CrNiMo1713	–	SCS16,	03Ch17N14M2
	00Cr19Ni13Mo3	317L	1.4438	X2CrNiMo17133	317S12	–	2367	Z2CND19.15	X2CrNiMo18.16	–	SUS317L	–
	–	329L	1.4460	X8CrNiMo275	–	–	2324	–	–	–	SUS329L; SCH11; SCS11	–
	1Cr18Ni9Ti	321	1.4541	X6CrNiTi1810	2337	321S12	58B	Z6CNT18.10	X6CrNiTi1811	F.3553	SUS321	12Ch18N10T
	1Cr18Ni11Nb	347	1.4550	X6CrNiNb1810	347S17	58F	2338	Z6CNNb18.1	X6CrNiTi1811	F.3552	SUS347	08Ch18N12B
	Cr18Ni12Mo2Ti	316Ti	1.4571	X6CrNiMoTi17122	320S17	58J	2350	Z6NDT17.12	X6CrNiMoTi17	F.3535	–	10Ch17N13M2T

Comparison table materials

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/ SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
M	**Austenitic stainless steel**											
	–	–	1.4581	G–X5CrNiMoNb1810	318C7	–	–	Z4CNDNb1812M	XG8CrNiMo18	–	SCS22	–
	Cr17Ni12Mo3Nb	318	1.4583	X10CrNiMoNb1812	–	–	–	Z6CNDNb1713B	X6CrNiMoTiNb17	–	–	–
	1Cr23Ni13	309	1.4828	X15CrNiSi2012	309S24	–	–	Z15CNS20.1	–	–	SUH309	20Ch20N14S2
	0Cr25Ni20	310S	1.4845	X12CrNi2521	310S24	–	2361	Z12CN2520	X6CrNi2520	F.331	SUH310	20Ch23N18
	Cr15Ni36W3Ti	330	1.4864	X12NiCrSi3616	–	–	–	Z12CNS35.1	–	–	SUH330	–
	–	–	1.4865	G–X40NiCrSi3818	330C11	–	–	–	XG50NiCr3919	–	SCH15	–
	5Cr2Mn9Ni4N	EV8	1.4871	X53CrMnNiN219	349S54; 321S12	– 58B	–	Z52CMN21.0	X53CrMnNiN219	–	SUH35	55Ch20G9AN4
	1Cr18Ni9Ti	321	1.4878	X12CrNiTi189	321S320	58C	–	Z6CNT18.12	X6CrNiTi1811	F.3523	SU321	09Ch18N10T

ISO	Country and standard									
	China	USA	Germany	Great Britain	Sweden	France	Italy	Spain	Japan	Russia
K	**Nodular cast iron**									
	QT400-18	60-40-18	GGG40	400/17	0717-02	FGS370-17	GS370-17	FGE38-17	FCD400	VC 42–12
	QT450-10	65-45-12	––	420/12	––	FGS400-12	GS400-12	FGE42-12	FCD450	–
	QT500-7	70-50-05	GGG50	500/7	0727-02	FGS500-7	GS500-7	FGE50-7	FCD500	VC 50–2
	QT600-3	80-60-03	GGG60	600/7	0732-03	FGS600-2	GS600-2	FGE60-2	FCD600	VC 60–2
	QT700-2	100-70-03	GGG70	700/2	0737-01	FGS700-2	GS700-2	FGE70-2	FCD700	VC 70–2
	QT800-2	120-90-02	GGG80	800/2	0864-03	FGS800-2	GS800-2	FGE80-2	FCD800	VC 80–2
	QT900-2	––	––	900/2	––	––	––	––	––	–
	Nodular cast iron									
	––	NO.60	GG40	––	0140	FGL400	––	––		Sc 40
	HT350	NO.50	GG35	350	0135	FGL350	G35	FG35	FC350	Sc 35
	HT300	NO.45	GG30	300	0130	FGL300	G30	FG30	FC300	Sc 30
	HT250	NO.35	GG25	250	0125	FGL250	G25	FG25	FC250	Sc 25
	HT200	NO.30	GG20	200	0120	FGL200	G20	FG20	FC200	Sc 20
	HT150	NO.20	GG15	150	0115	FGL150	G15	FG15	FC150	Sc 15
	HT100	––	––	100	0110	––	G10	––	FC100	–

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
H	**Hardened materials**											
	–	440A	1.4108	X100CrMo03	–	–	2258 08	–	–	–	C4BS	–
	–	610	1.4111	X100CrMoV15	–	–	2534 05	–	–		AC4A	–
	–	0-2	–	X65CrMo14	–	–	2541 06	–	–		AC4A	–

Comparison table materials

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
N	**Aluminium-based alloys**											
	–	SC64D	3.2373	G-AlSi9MgWA			4251	A-S7G			C4BS	–
	–	DG-AlSi12		G-ALMG5	LM5		4252	A-SU12			AC4A	
	–	356.1			LM25		4244				A5052	
	–	A413.0		GD-AlSi12			4247				A6061	
	–	A380.1		GD-AlSi8Cu3	LM24		4250				A7075	
	–	A413.1		G-AlSi12(Cu)	LM20		4260				ADC12	
	–	A413.2		G-AlSi12	LM6		4261					
	–	A360.2		G-AlSi10Mg(Cu)	LM9		4253					

ISO	Country and standard											
	China	USA	Germany		Great Britain		Sweden	France	Italy	Spain	Japan	Russia
	GB	AISI/SAE	W.-nr	DIN	BS	EN	SS	AFNOR	UNI	UNE	JIS	GOST
S	**Nickel based alloys**											
	–	5391	LW2 4670	S-NiCr13A16MoNb	mar-46	–	–	NC12AD	–	–		
	–	AMS 5397	LW2 4674	NiCo15Cr10MoAlTi	–	–	–	–	–	–		
	–	5660	LW2.4662	NiFe35Cr14MoTi	–	–	–	ZSNCDT42	–	–		
	–	5383	LW2.4668	NiCr19Fe19NbMo	HR8	–	–	NC19eNB	–	–		
	–	–	2.4631	NiCr20TiAk	Hr401.601	–	–	NC20TA	–	–		–
	–	AMS 5399	2.4973	NiCr19Co11MoTi	–	–	–	NC19KDT	–	–		–
	–	AMS 5544	LW2.4668	NiCr19Fe19NbMo	–	–	–	NC20K14	–	–		
	–	5390A	2.4603	–	–	–	–	NC22FeD	–	–		–
	–	5666	2.4856	NiCr22Mo9Nb	–	–	–	NC22FeDNB	–	–		–
	–	–	2.4630	NiCr20Ti	HR5.2034	–	–	NC20T	–	–		–
	–	4676	2.4375	NiCu30AL3Ti	3072-76	–	–	–	–	–		–
	Cobalt based alloys											
	–	5537C AMS		CoCr20W15Ni	–	–	–	KC20WN	–	–		
	–	5772	LW2.4964	CoCr20W14Ni				KC22WN				
	Titanium alloys											
	–	UNS R54520	3.7115.1	TiAl5Sn2.5	TA14/17	–	–	T-A5E	–	–		
	–							UNS R56400				
	–	–	3.7165.1	TiAl6V4	TA10-13/ TA28		–	UNS R56401	T-A6V	–	–	
	–			TiAl5V5Mo5Cr3								
	–	–	3.7185	TiAl4Mo4Sn4Si0.5	–	–	–	–	–	–		

Comparison table hardness and tensile strength

Hardness				Tensile strength N/mm²
Rockwell Hardness		Vickers Hardness	Brinell Hardness	
HRC	HRA	HV	HB	
70.0	86.6	1037	—	—
69.5	86.3	1017	—	—
69.0	86.1	997	—	—
68.5	85.8	978	—	—
68.0	85.5	959	—	—
67.5	85.2	941	—	—
67.0	85.0	923	—	—
66.5	84.7	906	—	—
66.0	84.4	889	—	—
65.5	84.1	872	—	—
65.0	83.9	856	—	—
64.5	83.6	840	—	—
64.0	83.3	825	—	—
63.5	83.1	810	—	—
63.0	82.8	795	—	—
62.5	82.5	780	—	—
62.0	82.2	766	—	—
61.5	82.0	752	—	—
61.0	81.7	739	—	—
60.5	81.4	726	—	—
60.0	81.2	713	—	2555
59.5	80.9	700	—	2500
59.0	80.6	688	—	2450
58.5	80.3	676	—	2395
58.0	80.1	664	—	2345
57.5	79.8	653	—	2295
57.0	79.5	642	—	2250
56.5	79.3	631	—	2205
56.0	79.0	620	—	2160
55.5	78.7	609	—	2115
55.0	78.5	599	—	2075
54.5	78.2	589	—	2035
54.0	77.9	579	—	1995
53.5	77.7	570	—	1955
53.0	77.4	561	—	1920
52.5	77.1	551	—	1885
52.0	76.9	543	—	1850
51.5	76.6	534	—	1815

Hardness				Tensile strength N/mm²
Rockwell Hardness		Vickers Hardness	Brinell Hardness	
HRC	HRA	HV	HB	
51.0	76.3	525	501	1780
50.5	76.1	517	494	1750
50.0	75.8	509	488	1720
49.5	75.5	501	481	1690
49.0	75.3	493	474	1660
48.5	75.0	485	468	1630
48.0	74.7	478	461	1605
47.5	74.5	470	455	1575
47.0	74.2	463	449	1550
46.5	73.9	456	442	1525
46.0	73.7	449	436	1500
45.5	73.4	443	430	1475
45.0	73.2	436	424	1450
44.5	72.9	429	418	1430
44.0	72.6	423	413	1405
43.5	72.4	417	407	1385
43.0	72.1	411	401	1360
42.5	71.8	405	396	1340
42.0	71.6	399	391	1320
41.5	71.3	393	385	1300
41.0	71.1	388	380	1280
40.0	70.8	382	375	1260
40.0	70.5	377	370	1245
39.5	70.3	372	365	1225
39.0	70.0	367	360	1210
38.5	—	362	355	1190
38.0	—	357	350	1175
37.5	—	352	345	1160
37.0	—	347	341	1140
36.5	—	342	336	1125
36.0	—	338	332	1110
35.5	—	333	327	1095
35.0	—	329	323	1080
34.5	—	324	318	1065
34.0	—	320	314	1050
33.5	—	316	310	1035
33.0	—	312	306	1020
32.5	—	308	302	1010

Comparison table hardness and tensile strength

Hardness				Tensile strength N/mm²	Hardness				Tensile strength N/mm²
Rockwell Hardness		Vickers Hardness	Brinell Hardness		Rockwell Hardness		Vickers Hardness	Brinell Hardness	
HRC	HRA	HV	HB		HRC	HRA	HV	HB	
32.0	—	304	298	995	24.0	—	249	245	820
31.5	—	300	294	980	23.5	—	246	242	810
31.0	—	296	291	970	23.0	—	243	240	800
30.5	—	292	287	960	22.5	—	240	237	790
30.0	—	289	283	950	22.0	—	237	234	785
29.5	—	285	280	935	21.5	—	234	232	775
29.0	—	281	276	920	21.0	—	231	229	765
28.5	—	278	273	910	20.5	—	229	227	760
28.0	—	274	269	900	20.0	—	226	225	750
27.5	—	271	266	890	19.5	—	223	222	745
27.0	—	268	263	880	19.0	—	221	220	735
26.5	—	264	260	870	18.5	—	218	218	730
26.0	—	261	257	860	18.0	—	216	216	725
25.5	—	258	254	850	17.5	—	214	214	715
25.0	—	255	251	835	17.0	—	211	211	710
24.5	—	252	248	830					

Note: The conversion values for steel in the table are commonly applicable for the steels with carbon from low to high.

Examples of materials for machining groups

Material No.	Material	Machining group
1.0722	10SPb20	1
1.0715	9SMn28	1
1.0736	9SMn36	1
1.0718	9SMnPb28	1
1.0737	9SMnPb36	1
1.0401	C15	1
1.0402	C22	1
1.1141	Ck15	1
1.1170	28Mn6	2
1.0726	35S20	2 / 3
1.1167	36Mn5	2 / 3
1.1157	40Mn4	2 / 3
1.0501	C35	2 / 3
1.0503	C45	2 / 3
1.1191	Ck45	2 / 3
1.1183	Cf35	2 /3
1.1213	Cf53	2 /3
1.1545	C 105 W1	4 / 5
1.1663	C 125 W	4 / 5
1.0535	C55	4 / 5
1.0601	C60	4 / 5
1.1274	Ck101	4 / 5
1.1203	Ck55	4 / 5
1.1221	Ck60	4 / 5
1.5710	36NiCr6	5 / 9
1.5120	38MnSi 4	5 / 9
1.1545	C 105 W2	4 / 5
1.1663	C 125 W	4 / 5
1.0535	C65	4 / 5
1.0601	C70	4 / 5
1.1274	Ck101	4 / 5
1.1203	Ck55	4 / 5
1.1221	Ck60	4 / 5
1.5710	36NiCr7	5 / 9
1.5120	38MnSi 5	5 / 9
1.1545	C 105 W3	4 / 5
1.1663	C 125 W	4 / 5
1.0535	C75	4 / 5
1.0601	C80	4 / 5
1.1274	Ck101	4 / 5
1.1203	Ck55	4 / 5
1.1221	Ck60	4 / 5
1.5710	36NiCr8	5 / 9
1.5120	38MnSi 6	5 / 9
1.1545	C 105 W4	4 / 5
1.1663	C 125 W	4 / 5
1.0535	C85	4 / 5
1.0601	C90	4 / 5
1.1274	Ck101	4 / 5

Material No.	Material	Machining group
1.1203	Ck55	4 / 5
1.1221	Ck60	4 / 5
1.5710	36NiCr9	5 / 9
1.5120	38MnSi 7	5 / 9
1.1545	C 105 W5	4 / 5
1.1663	C 125 W	4 / 5
1.0535	C95	4 / 5
1.0601	C100	4 / 5
1.1274	Ck101	4 / 5
1.1203	Ck55	4 / 5
1.1221	Ck60	4 / 5
1.5710	36NiCr10	5 / 9
1.5120	38MnSi 8	5 / 9
1.5680	12Ni19	10 / 11
1.3255	S 18-1-2-5	10 / 11
1.3348	S 2-9-2	10 / 11
1.3343	S 6-5-2	10 / 11
1.3243	S 6-5-2-5	10 / 11
1.2363	X 100 CrMoV 5-1	10 / 11
1.2601	X165CrMoV12	10 / 11
1.2080	X210 Cr 12	10 / 11
1.2581	X30WCrV 9-3	10 / 11
1.2344	X40CrMoV 5-1	10 / 11
1.4718	X45CrSi9-3	10 / 11
1.3355	S 18–0–1	10 /11
1.4027	G–X20Cr14	12 / 13
1.4006	X12 Cr 13	12 / 13
1.4104	X12CrMoS 17	12 / 13
1.4057	X19CrNi 17-2	12 / 13
1.4034	X46Cr 13	12 / 13
1.4871	X53 CrMnNiN 21-9	12 / 13
1.4113	X6CrMo 17	12 / 13
1.4000	X6CR 13	12 / 13
1.4001	X7Cr14	12 / 13
1.4016	X6Cr17	12 / 13
1.4581	G–X5CrNiMoNb 18	14
1.4308	G–X6CrNi 18-9	14
1.4408	G–X6CrNiMo 18-10	14
1.4583	X6CrNiMoNb 18-12	14
1.4571	X6CrNiMoTi 17-12-2	14
1.4550	X6CrNiNb 18-10	14
1.4541	X14CrNiTi 18-10	14
1.4845	X12CrNi 25-21	14
1.4310	X10CrNi 18-8	14
1.4305	X10CrNiS 18-10	14
1.4878	X12CrNiTi 18-9	14
1.4317	X2CrNi 18-8	14
1.4436	X3CrNiMo 17-13-3	14
1.4440	X2CrNiMo 18-16	14

Material No.	Material	Machining group
1.4429	X2CrNiMoN 17-13-3	14
1.4311	X2CrNiN 18-10	14
1.4301	X5CrNi 18-10	14
1.4401	X5CrNiMo 17-12-2	14
0.6010	GG10	16
0.6015	GG15	16
0.6020	GG20	16
0.6025	GG25	16 / 17
0.6030	GG30	17
0.6035	GG35	17
0.6040	GG40	17
1.4829	X12NiCrSi 22-12	17
1.4828	X15CrNiSi20-12	17
0.7033	GGG35.3	18
0.7040	GGG40	18
0.7043	GGG40.3	18
0.8135	GTS-35	18
0.7050	GGG50	19
0.7060	GGG60	19
0.7070	GGG70	19
0.7660	GGGNiCr 20-2	19
0.7652	GGGNiMn 13-7	19
0.8155	GTS-55	21
0.8165	GTS-65	21
0.8170	GTS-70	21
0.8145	GTS-45	21
3.0205	Al99	22
3.3315	AlMg 1	22
3.1325	AlCuMg 1	23
3.2315	AlMgSi 1	23
3.2581	G-AlSi12	24
3.2163	G-AlSi9Cu3	24
3.2381	G-AlSi10Mg	25
2.0375	CuZn36Pb 3	27
2.1096	G-CuSn5ZnPb	27
2.0590	G-CuZn40Fe	27
2.0240	CuZn15	28
2.0060	E-Cu 57	29
1.4865	G-X40NiCrSi 38-18	30
1.4864	X12NiCrSi 36-16	30
2.4631	NiCr20TiAl	32
2.4856	NiCr22Mo9Nb	32
2.4375	NiCu30Al	33
2.4955	NiFe25Cr20NbTi	33
2.4764	CoCr20W15Ni	34
1.3401	G-X120Mn12	34
3.7165	TiAl6V4	36

Torque for screw

Thread	M1,6	M1,8	M2	M2,2	M2,5	M3	M3,5	M4	M4,5	M5	M6	M7	M8	M10	M12
Torque [Nm]	0,2	0,3	0,4	0,7	0,8	1,5	2,3	3,4	5,0	6,7	11,4	19,2	27,0	55,8	85